

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 December 2006 (14.12.2006)

PCT

(10) International Publication Number
WO 2006/133259 A2

(51) International Patent Classification:
B32B 3/24 (2006.01)

28766 (US). STROUD, Herbert, D., Jr. [US/US]; 122
Muscadine Ridge, Rutherfordton, NC 28139 (US).

(21) International Application Number:
PCT/US2006/022063

(74) Agents: ASHLEY, Stephen, S. et al.; ADAMS EVANS
P.A., 2180 Two Wachovia Center, 301 South Tryon Street,
Charlotte, NC 28282 (US).

(22) International Filing Date: 6 June 2006 (06.06.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/687,676 6 June 2005 (06.06.2005) US


(71) Applicant (for all designated States except US): BLUE
RIDGE MICRO-PERF, LLC [US/US]; RR#1 Box 91B,
Penrose, NC 28766 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV,
LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI,
NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG,
SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: MICRO-PERFORATED LAMINAE AND METHOD



(57) Abstract: A micro-perforated laminae includes a layer of material having a plurality of spaced-apart perforations, in which the total open orifice area of the perforations is about 0.1 % to 17.0% of the total surface area of the layer of material. The layer of material can be a thermoplastic material, metal foil, cellulosic film, paper and/or nonwoven. The perforations can be slits, with each slit having a length of no more than about 100 mils (2.54 mm). Alternatively, the perforations can be holes, in which each hole has a diameter of no more than about five mils (0.13 mm). The total open orifice area of perforations can be in the range of about 0.1 mm² to about 17 mm² per square centimeter of the total surface area of the micro-perforated laminae.

WO 2006/133259 A2